

# FICHE TECHNIQUE

Nom du produit : SILICATE DE ZIRCONIUM

<b>Caratteristiche fisiche e chimiche</b> <i>Physical and chemical characteristics</i>		
<b>ZIRCOBIT MO - ZRU 1</b>		
<b>Analisi Chimica <sup>(1)</sup></b> <i>Chemical Analysis</i>	<b>Tipica (%)</b> <i>Typical</i>	<b>Garantita (%)</b> <i>Guaranteed</i>
ZrO <sub>2</sub> + HfO <sub>2</sub>	64,8 ± 0,5	63,5 min
SiO <sub>2</sub>	32,5 ± 0,5	34 max
Al <sub>2</sub> O <sub>3</sub>	1,2 ± 0,5	2,5 max
TiO <sub>2</sub>	0,15 ± 0,03	0,25 max
Fe <sub>2</sub> O <sub>3</sub>	0,07 ± 0,01	0,1 max
K <sub>2</sub> O	n.d.	n.d.
LOI <sup>(2)</sup>	0,6 ± 0,2	1,0 max
<b>Granulometria <sup>(3)</sup></b> <i>Particle Size</i>	D50 = 1,43 ± 0,16 μm	
<b>Attività Specifica γ <sup>(4)</sup></b> <i>Specific Activity γ</i>	$^{226}\text{Ra} \leq 4,3 \text{ Bq/g}$ $^{232}\text{Th} \leq 1,0 \text{ Bq/g}$ $^{226}\text{Ra} + ^{232}\text{Th} \leq 5,0 \text{ Bq/g}$	
<b>Metodo</b> <i>Method</i>	<sup>(1)</sup> IOS 14/02/03 Industrie Bitossi S.p.A. Ed. in vigore/currently used <sup>(2)</sup> IOS 16/02/03 Industrie Bitossi S.p.A. Ed. in vigore/currently used <sup>(3)</sup> IOS 01/02/03 Industrie Bitossi S.p.A. Ed. in vigore/currently used <sup>(4)</sup> IOS 17/02/03 Industrie Bitossi S.p.A. Ed. in vigore/currently used	